



# Microseal Industries Inc.

## CT-35HP™ *COVER TAPE*



### **Description**

A clear, anti-static, heat activatable Cover Tape, for use with tapes made of polystyrene.

**CT-35HP™** is designed to adhere at various temperatures and dwell times within industry standards.

For stronger adhesion, use a combination of higher temperature, longer dwell time and/or increased pressure.

### **Dimensions**

**CT-35HP™** Cover Tape is wound on a 3" plastic core in all standard widths. Splice free rolls are available in 300 meter lengths. Custom widths and lengths are available upon request.

### **Storage**

Store at controlled room temperature 19° C to 40° C (66° F to 104° F).

Relative Humidity 50 ± 30%. Best if used within 24 months. Avoid excessive heat.

610 E. 36 Street, P.O Box 3054  
Paterson, NJ 07509-3054  
Phone: 973.523.0704  
Fax: 973.279.6916  
Email: [info@covertape.com](mailto:info@covertape.com)

For additional information  
please visit us at:  
**COVERTAPE.COM**



# Microseal Industries Inc.

## CT-35HP™ COVER TAPE



### Recommended Sealing Conditions

Temperature Range..... 165° - 210° C  
 Dwell time.....0.1 - 1.0 seconds  
 Shoe width..... 0.015 - 0.020 inches  
 Pressure..... 30 psi

Properties	Value	Test Method
Surface Resistivity	<math>10^{12}> \geq 10^5</math> Ohms/square, (both sides)	ASTM D-257
Tribo - Electric charge generation, adhesive tape pull test Static Decay 5kv	Less Than 50 volts Less than .1 seconds	EIA -541 Mil B-81705
<b>Clarity</b> Luminous Transmittance Haze Clarity	93 % 51 % 35 %	ASTM D1003
<b>Strength</b> Tensile Strength MD Elongation at Break MD	11,000 psi 120 -140%	ASTM D882A ASTM D882A
<b>Peel</b>	50 gms $\pm$ 20	EIA 481B

### Performance Characteristics

CT-35HP™ is ideally suited to adhere to polystyrene carrier.

610 E. 36 Street, P.O Box 3054  
 Paterson, NJ 07509-3054  
 Phone: 973.523.0704  
 Fax: 973.279.6916  
 Email: info@covertape.com

For additional information  
 please visit us at:  
**COVERTAPE.COM**